Polyurethane Foams

GM-M Series-Medium Firmness

Medium firmness Polyurethane Foams for industry application.


Benefits

- Reduce shock and isolate vibration
- Long term spring force
- Super compression set resistance
- Good sealing performance

Applications

- Environmental seals
- Vibration isolator
- Shock absorption pad

Naming




Storage

Store in a dry and cool place

No direct exposed to UV or solvent

Properties	Test Method	GM-M24	GM-M32	GM-M48
Density, kg/m³(lb/ft³) Tolerance,%	ASTM D3574 Test A	240(15) ±10	320(20) ±10	480(30) ±10
Thickness,mm Tolerance		1.0~8.0 ±10%	0.5~6.0 ±10%	0.3~4.0 ±10%
Compression Set % max, 50%, 70°C	ASTM D3574 Test D	10		
Compression Force Deflection, Range Kpa, Typical Kpa	ASTM D3574 Test C. 25% deflection	30~55 40	50~90 75	100~260 170
Color		Black		
Recommended Constant Use, max		90°C		
Recommended Intermittent Use, max		120°C		



Dongguan GuangMai Electronics Technology Co.,Ltd

Tel:0769-26621791

Fax:0769-26621791